

Technical Data Sheet

Secondary Insulation

Ripley™ E 468-2-7FC-55F
(E 468-2-7FC Fast Cure Filled Impregnant)

Single-Component Epoxy VPI Resin

Ripley™ E 468-2-7FC-55F

Product Description

Ripley™ E 468-2-7FC-55F is a single-component, heat-cured, 100% solids epoxy impregnating resin.

Areas of Application

The Ripley™ E 468 product line is the industry standard for impregnation of transformers of all sizes

Features and Benefits

- Mineral filled for improved heat dissipation
- Flexible for excellent noise suppression
- No catalyst required
- High flash point
- UL recognized insulation systems up to Class 240

Application Methods

- Vacuum-Pressure Impregnation
- Vacuum Impregnation

Transportation / Storage

Store below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for six (6) months from the date of shipment.

Usable life may be extended by refrigerated storage at 5°C / 41°F.

For best results, VPI storage tanks should have a replenishment rate of 10% or more per month and employ cooling systems to maintain the resin at 20°C / 68°F or below.

Mix thoroughly before use

Health / Safety

Refer to the Material Safety Data Sheet.

Typical Properties of Material as Supplied

Property	Conditions	Value	Units
Viscosity	25°C / 77°F	4000 – 8000	cP
Weight per Gallon	25°C / 77°F	12.8 – 13.2	pounds
Sunshine Gel Time	135°C / 275°F	12 – 20	minutes
Flash Point	ASTM D93	> 94 > 201	°C °F

Curing Schedule

Preheat units, as necessary, to remove moisture and set tapes. Allow units to cool to below 30°C / 86°F before immersion to promote good penetration while not overheating the resin.

Cure VPI-treated units for 4 hours at 135°C / 275°F – or –
3 hours at 150°C / 302°F

Cure schedule is based on time after unit reaches specified temperature

Ripley™ E 468-2-7FC-55F

Typical Mechanical Properties

Specimens cured 4 hours at 135°C / 275°F

Property	Conditions	Value	Units
Tensile Strength ASTM D638	25°C / 77°F	2400	psi
Elongation ASTM D638	25°C / 77°F	20	%
Hardness – Shore D	25°C / 77°F	65 – 75	
Glass Transition Temp.	TMA	47 – 52	°C
Coefficient of Thermal Expansion	Below Tg	63	ppm / °C
Coefficient of Thermal Expansion	Above Tg	142	ppm / °C

Typical Electrical Properties

Property	Conditions	Value	Units
Dielectric Strength ASTM D149	0.5 mils – 25°C / 77°F	2000	volts/mil
Dielectric Strength ASTM D149	0.5 mils – 25°C / 77°F After 24 hours in water	1400	volts/mil
Dissipation Factor ASTM D150	1 kHz – 25°C / 77°F	0.01	
Dielectric Constant ASTM D150	1 kHz – 25°C / 77°F	3.4	
Volume Resistivity ASTM D257	25°C / 77°F	7.0×10^{15}	ohm-cm

Ripley™ E 468-2-7FC-55F

UL Recognized Insulation Systems (ELANTAS File E87039)

Thermal Class	System
Class 130	DASH 2: B-1, B-2, B-2Z, B-2Z-1, B-5, B-8, B-10, B-11, B-13, B-14, B-19, BR-1, BR-2, PDG 12, PDG 116
Class 155	DASH 2: F-1, F3, F4, F-4A, PDG 117
Class 180	DASH 2: H-1, H-2, H-3, H-4, H-5, H-8, HR-1, HR-2, HR-3, HR-4, PDG 14, PDG 180 High Voltage
Class 200	DASH 2: N-1, N-2, N-3, N-4, N-6, N-2HV, PDG 10, MEGA IV
Class 220	DASH 2: R-1, R-2, R-3, R-5, HV-1, HV-2, PDG 8, PDG 220-1, PDG 220 High Voltage, PDG 15
Class 240	DASH 2: S-1

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing a product and no such representation should be relied upon.