

Catalogue

Catalogue

Sterling

Product	Y-210	
Feature-Advantage-Benefit	Industry Standard, Excellent tank stability	
Type	Alkyd	
Reducer, monomer	Xylene	
%NVM	46-50	
Flash Point (°C)	30	
Viscosity @25°C	150-250	
Cure Cycle	Time (H)	2-4
	Temp.(°C)	150-170
Dielectric Strength (volts/mil)	Dry	4000
	Wet	3800
Bond strength (ASTM D 2519)	25°C	27
	150°C	3
UL	Yes	